

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C11D 3/22, D06L 1/12</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/64551</b> <b>(43) International Publication Date:</b> 16 December 1999 (16.12.99)
<b>(21) International Application Number:</b> PCT/NL99/00361 <b>(22) International Filing Date:</b> 10 June 1999 (10.06.99)  <b>(30) Priority Data:</b> 1009368 10 June 1998 (10.06.98) NL  <b>(71) Applicants (for all designated States except US):</b> COÖPERATIE COSUN U.A. [NL/NL]; Zuilenstraat 100, NL-4814 ND Breda (NL). SYBRON CHEMIE NEDERLAND B.V. [NL/NL]; Einsteinstraat 11, NL-6716 AC Ede (NL).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> KUZEE, Hendrika, Cornelia [NL/NL]; Bermweg 51, NL-4388 CB Oost-Souburg (NL). RAAIJMAKERS, Henricus, Wilhelmus, Carolina [NL/NL]; Hoveniersberg 33, NL-4708 HD Roosendaal (NL). BOLKENBAAS, Mariëtte, Ellen, Boukje [NL/NL]; Groene-Poort 3, NL-3704 AA Oosterland (NL). KAARS-GAREN, Antonius, Jacobus, Gerardus, Maria [NL/NL]; Catharinadaal 104, NL-6715 KD Ede (NL). KOOI, Johannes [NL/NL]; Broekhofsestraat 11, NL-5437 BA Beers (NL). FLIERVOET, Hildegonda, Petronella, Maria [NL/NL]; Opaalstraat 20, NL-6713 VD Ede (NL).		<b>(74) Agent:</b> OTTEVANGERS, S., U.; Vereenigde Octrooibureaux, Nieuwe Parklaan 97, NL-2587 BN The Hague (NL).  <b>(81) Designated States:</b> AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> METHOD FOR TREATING TEXTILE  <b>(57) Abstract</b>  The present invention relates to a method for removing contaminants from textile, wherein the textile is treated with a fructan polycarboxylic acid which contains on average at least 0.05 carboxyl groups per monosaccharide unit. The present invention provides a particularly environment-friendly method, by which various contaminants can be efficiently removed from textile.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Title: Method for treating textile

This invention relates to a method for treating textile and more particularly to a method for removing contaminants from textile.

In the textile processing industry, it is usual to  
5 process raw materials whose origin is not precisely known. Cotton and wool, for instance, are often purchased in the form of semimanufactured products which still contain various contaminants. In the case of cotton, those  
10 contaminants often consist of particles, such as sand and small plant remains, pigment particles and residues of plant protection agents and defoliants. In wool, the contaminants referred to can consist of soil or sand, or feces, urine, sweat, and greases (lanolin) originating from the animal from which the wool is derived.

15 As the textile processing industry often does not know of each batch of textile semimanufactured product which contaminants are present in it, the aim is to have processes available that are as universal as possible and by which different kinds of contaminants can be removed in  
20 a single step. In practice, for this reason, textile is normally treated with a composition comprising a polyacrylate.

A disadvantage of the known compositions based on polyacrylates is that polyacrylates are hardly, if at all,  
25 biodegradable. These substances are discharged along with the washing water used in the treatments. When the waste water is processed in a water purification plant, the polyacrylates end up in the sludge left, and thus end up in the environment.

30 It is an object of the invention to provide a method for treating textile, whereby contaminants are removed in an efficient manner and whereby the environment is not unacceptably burdened.

Surprisingly, it has now been found that the use of certain specific fructan polycarboxylic acids leads to a highly efficient, environment-friendly removal of contaminants from textile. Accordingly, the invention  
5 relates to a method for removing contaminants from textile, wherein the textile is treated with a fructan polycarboxylic acid which contains on average at least 0.05 carboxyl groups per monosaccharide unit.

It is of great advantage in a method according to  
10 the invention that the materials used are biodegradable. The fructan polycarboxylic acids used according to the invention have the property that they are broken down within a relatively short time to substances that are preferably water-soluble and non-toxic. The decomposition  
15 can occur *inter alia* by hydrolytic splitting, under the influence of light, air, water and/or microorganisms occurring in nature. Because of this property, the materials are designated by the term biodegradable materials.

20 In addition, it has been found that with the use of the present fructan polycarboxylic acids, an attractive alternative to the conventionally used polyacrylates is also being offered as regards the effectiveness in the removal of contaminants.

25 As stated, according to the invention, textile is treated with a fructan polycarboxylic acid which contains on average at least 0.05 carboxyl groups per monosaccharide unit. Depending on the nature of the fructan polycarboxylic acid, the number of carboxyl groups per monosaccharide unit  
30 of the fructan polycarboxylic acid can be expressed in the total degree of substitution of carboxyl groups (DS) or the total degree of oxidation (DO). Preferably, the fructan polycarboxylic acid to be used contains between 0.5 and 3 carboxyl groups per monosaccharide unit. It will be clear  
35 that it is also possible according to the invention to use mixtures of different fructan polycarboxylic acids.

A fructan polycarboxylic acid is understood to mean any oligo- or polysaccharide that contains a plurality of anhydrofructan units and which has been converted into a polycarboxylic acid. The fructans on which a fructan  
5 polycarboxylic acid can be based can have a polydisperse chain length distribution and can have a linear or branched chain. Preferably, the fructans contain mainly  $\beta$ -1,2 bonds, as in inulin, but they may also contain  $\beta$ -2,6 bonds, as in levan. Suitable fructans can originate directly from a  
10 natural source, but may also have undergone a modification. Examples of modifications in this connection are reactions, known per se, which lead to a lengthening or shortening of the chain length. Suitable fructans have an average chain length (degree of polymerization, DP) of at least 2, up to  
15 about 1,000. Preferably, a fructan is used having a degree of polymerization of at least 3, more preferably at least 6, most preferably at least 10, up to about 60.

Fructans on which a fructan polycarboxylic acid can be based for use in a method according to the invention  
20 include, in addition to naturally occurring polysaccharides, industrially prepared polysaccharides, such as hydrolysis products, which have shortened chains, and fractionated products having a modified chain length, in particular a chain length of at least 10. A hydrolysis  
25 reaction for obtaining a fructan having a shorter chain length can be carried out enzymatically (for instance with endoinulinase), chemically (for instance with aqueous acid), physically (for instance thermally) or by the use of heterogeneous catalysis (for instance with an acid ion  
30 exchanger). Fractionation of fructans, such as inulin, can be accomplished, for instance, by crystallization at low temperature, separation with column chromatography, membrane filtration, and selective precipitation with an alcohol. Other fructans, such as fructans having a long  
35 chain, can be obtained, for instance, by crystallization, from fructans from which mono- and disaccharides have been

removed, and fructans whose chain length has been enzymatically extended can also serve as a basis for a fructan polycarboxylic acid that is used in the present method. Further, reduced fructans can be used. These are  
5 fructans whose reducing terminal groups, normally fructose groups, have been reduced, for instance with sodium borohydride or hydrogen in the presence of a transition metal catalyst. Also eligible for use are fructans which have been chemically modified, such as crosslinked fructans  
10 and hydroxyalkylated fructans.

In a preferred embodiment, the fructan polycarboxylic acid which is used according to the invention is based on inulin. Inulin is a polysaccharide consisting of  $\beta$ -1,2 bound fructose units with an  $\alpha$ -D-glucopyranose unit at the  
15 reducing end of the molecule. The substance occurs *inter alia* in the roots and tubers of plants of the *Liliaceae* and *Compositae* families. The most important sources for the production of inulin are Jerusalem artichoke, dahlia and chicory root. In the industrial production of inulin, the  
20 starting material is mainly chicory root. The principal difference between inulins originating from the different natural sources resides in the degree of polymerization, which may vary from about 6 in Jerusalem artichokes to 10-14 in chicory roots and higher than 20 in dahlias.  
25 According to the invention, it is preferred to use a fructan polycarboxylic acid having a degree of polymerization of 9-11.

The derivatives of inulin used according to the invention are polycarboxylates. Known suitable  
30 polycarboxylate derivatives of inulin are dicarboxy inulin, obtained, for instance, by glycolytic oxidation of inulin, 6-carboxy-inulin, obtained, for instance, by selective oxidation of the primary hydroxyl groups of inulin (TEMPO oxidation), carboxymethyl inulin, carboxyethyl inulin,  
35 obtained, for instance, by cyanoethylation followed by hydrolysis. Derivatives of inulin which are preferably used

are dicarboxy inulin, carboxymethyl inulin and carboxyethyl inulin.

Particularly suitable fructan polycarboxylic acids for use in a method according to the invention are further  
5 fructan polycarboxylic acids that contain both carboxyl groups obtained by oxidation of carbon atoms forming part of the anhydrofructose units in the molecule, and carboxyl groups obtained by attachment of carboxyalkyl or carboxyacyl groups to the anhydrofructose units. It has  
10 been found that these twofold modified compounds are more suitable for removing contaminants from textile than may be expected on the ground of the combination of, for instance, dicarboxy inulin and carboxymethyl inulin.

The twofold modified fructan polycarboxylic acids  
15 mentioned can be prepared by oxidizing a fructan in a known manner, followed by carboxyalkylation or carboxyacylation of the oxidation product in a known manner. It is also possible to change this order around and to have carboxyalkylation or carboxyacylation precede oxidation.  
20 The carboxymethylation can be carried out, for instance, with sodium monochloroacetate in water at a pH of 10-13, or with another haloacetic acid derivative.

Dicarboxymethylation can be carried out in a comparable manner, for instance by reaction with a halomalonate ester,  
25 followed by hydrolysis. Carboxyacylation can be carried out with an anhydride or another reactive derivative of a polycarboxylic acid, such as succinic acid or maleic acid anhydride. The oxidation can be carried out in different ways, for instance utilizing hypohalite, periodate/chlorite  
30 or hydrogen peroxide, which in each case leads mainly to dicarboxyl groups ( $C_3$ - $C_4$  cleavage), or utilizing hypochlorite/TEMPO, which leads to monocarboxyl groups ( $C_6$  oxidation). Oxidation whereby  $C_3$ - $C_4$  cleavage occurs is preferred.

35 If a fructan is first carboxyalkylated or carboxyacylated, and then oxidized, the DS after this first

step is preferably not higher than 1.2, so that sufficient reactive sites are left in the fructan for the oxidation.

When subsequently a C<sub>6</sub> oxidation is carried out, the carboxyalkylation or carboxyacylation can be allowed to

5 proceed to a higher DS, for instance to a DS of 2.0.

Preferably, the fructan is first oxidized, for instance to a DS of at least 0.2, preferably to a DS between 0.5 and 2.0 (25-100% oxidation in the case of C<sub>3</sub>-C<sub>4</sub> oxidation). The oxidized product is thereupon

10 carboxyalkylated or carboxyacylated, for instance to a DS between 0.2 and 1.8, preferably to a DS between 0.5 and 1.6. If desired, the solution obtained after oxidation can be concentrated, so that the efficiency of the carboxyalkylation or carboxyacylation is increased. This  
15 leads to products where the carboxyalkyl or carboxyacyl groups are present in larger numbers at the positions of primary hydroxyl groups (C<sub>6</sub> in inulin and C<sub>1</sub> in levan) than under normal conditions in carboxyalkylated or carboxyacylated fructans. This means that at least 30%,  
20 preferably at least 40%, of the carboxyalkyl or carboxyacyl groups are present on primary carbon atoms.

In many cases, it is advantageous to use as starting material a fructan from which the reducing units have been removed through treatment with a reducing agent, such as  
25 sodium borohydride or hydrogen in combination with a transition metal catalyst. According to this preferred embodiment, a fructan polycarboxylic acid for the present use can be suitably prepared by reducing first, then oxidizing, followed by carboxyalkylation or  
30 carboxyacylation, and finally purifying.

Wherever in this text and the appended claims reference is made to carboxylic acids, these are always understood to include both the free acid and metal or ammonium salts of the carboxylic acid. The term  
35 carboxyalkyl refers to a C<sub>1</sub>-C<sub>4</sub> alkyl group substituted by one or more carboxyl groups, such as carboxymethyl,



carboxyethyl, dicarboxymethyl, 1,2-dicarboxyethyl and the like. The term carboxyacyl refers to a C<sub>1</sub>-C<sub>4</sub> acyl group, in particular a C<sub>1</sub>-C<sub>4</sub> alkanoyl or alkenoyl group substituted by one or more carboxyl groups, such as carboxyacetyl, 5  $\beta$ -carboxypropionyl,  $\beta$ -carboxyacryloyl,  $\gamma$ -carboxybutyryl, dicarboxyhydroxybutyryl, and the like. As regards the carboxyalkyl and carboxyacyl groups, a preference is expressed for carboxymethyl.

Further, it has been found to be of advantage to use a 10 fructan polycarboxylic acid in combination with an organic acid. The presence of an organic acid has been found to enhance the action of the fructan polycarboxylic acid in the removal of contaminants from textile. As organic acid, preferably glycol acid, diglycol acid or hydroxyacetic acid 15 is used.

According to the invention, textile is treated to remove contaminants present therein. Normally, this involves textile originating from a natural source, such as cotton, wool, jute, silk, linen and the like. However, a 20 method according to the invention can also be practiced in the case of textile based on synthetic fibers, such as polyesters and polyamides. Preferably, cotton, linen or wool are involved.

The contaminants that can be present in the textile 25 will be highly divergent in nature. As stated, frequently occurring contaminants in cotton are sand particles, dust particles and pigment particles, and plant protection agents. However, also during harvesting of the cotton, a number of contaminants, such as defoliants and plant 30 remains, may end up in the textile. As stated, in wool, which originates from an animal source, the contaminants will stem to a large extent from the wool-producing animal itself. In addition, often sand, soil or grass will be present in the wool. The contaminants that can be present 35 in textile based on synthetic fibers will often stem from the equipment used in manufacturing and/or processing the

textile. To be considered here are oil used for lubricating apparatus and size present on the warp of a loom for protecting the warp threads. A great advantage of a method according to the invention is further that the fructan  
5 polycarboxylic acid used eliminates the adverse effects of hard water (mainly calcium and magnesium ions).

Another contaminant that is removed from textile concerns non-covalently bound, reactive dyestuff. In applying reactive dyestuffs to textile, there occurs to  
10 some extent, in addition to the desired reaction whereby the dyestuff is covalently bound to the textile, an undesired hydrolysis reaction which leads to a product that cannot bind covalently to the textile. In addition, there will be a certain amount of reactive dyestuff that does not  
15 undergo any reaction at all. This excess dyestuff and the undesired by-product resulting from the hydrolysis referred to in fact constitute contaminants that are to be removed in a rewashing treatment. It has now been found that these contaminants too can be eminently removed in an  
20 ecologically sound manner in a method according to the invention.

The present method for removing contaminants from textile can find application in various stages and operations that are carried out in the textile industry.  
25 Treatments where good results have been achieved include washing, boiling down, bleaching, dyeing and rewashing. Below, these treatments, and how the present method can be applicable therein, will be discussed by way of example. It will be clear to one skilled in the art that various  
30 modifications in the processes mentioned below are possible. Accordingly, the processes described below should not be construed as limiting the invention.

Washing, in most cases, is the first treatment in a textile processing plant carried out on a batch of textile  
35 that has been purchased. The treatment applies to all

important kinds of textile, in particular to cotton, wool and linen, but also to synthetic fibers.

Cotton can be washed, for instance, to remove contaminants in a washing or dyeing machine of, for instance, 2,000 to 3,000 liters at a temperature between 60 and 100°C in a liquor ratio of from 1:5 to 1:20 (that is, from 5 to 20 liters of water per kg of textile substrate). Of the fructan polycarboxylic acid, preferably a 25-40% solution is metered in an amount of 0.5-3 g/l of water. Further added to the water are, preferably, alkali, for instance 1-3 g/l of soda or 1-5 g/l of NaOH, and an anionic or a non-ionic detergent, or a combination thereof.

Wool can be washed, for instance, to remove contaminants at a temperature of from 30 to 60°C in a liquor ratio between 1:5 and 1:20. Of the fructan polycarboxylic acid, preferably a 25-40% solution is metered in an amount of 1-3 g/l of water. It has been found to be of great advantage to add a certain amount of alkali in addition to the fructan polycarboxylic acid. As alkali, 1-3 g/l of soda or 1-3 ml/l of ammonia (25%), or triethanolamine can be used. Further, preferably, also 1-2 g/l of a non-ionic detergent will be used.

In washing linen to remove contaminants, it is of importance not to remove all hardness ions (mainly calcium and magnesium ions), since the fibrils which the long linen fibers form are kept together by calcium pectinate. It has been found that in the present method, this fibril structure is maintained and so-called cottonizing of the linen is prevented. The washing temperature will normally be between 60 and 100°C, while the liquor ratio used is preferably between 1:5 and 1:20. Preferably, a 25-40% solution of the fructan polycarboxylic acid is metered in an amount of 1-4 g/l of water. Depending on the desired feel variations, optionally sodium hydroxide or soda can be used as well, in an amount which can be readily optimized

by one skilled in the art. Further, also an anionic or non-ionic detergent, or a mixture of the two, will be used.

Synthetic fibers, such as polyamide or polyester fibers, can be washed to remove contaminants at a temperature of 20-90°C in a liquor ratio from 1:3 to 1:15. Preferably, a 25-40% solution of the fructan polycarboxylic acid is metered in an amount of 1-2 g/l of water. Although less common in washing synthetic textile, it may be advantageous in certain cases to add 1-2 g/l of soda or sodium hydroxide. Further, preferably 1-2 g/l of a non-ionic detergent is used.

In view of the high temperatures normally used in boiling down textile, this treatment will be applied only to textile that is resistant to high temperatures, such as linen or cotton. The temperature in boiling down cotton is preferably between 90 and 130°C, while preferably 1 to 15 liters of water per kg of textile are used. Boiling down can be carried out in different apparatuses.

If a washing/dyeing machine where the textile is in motion is used, the duration of the treatment will be between 30 and 90 minutes. Preferably, the treatment then lasts about 60 minutes at a temperature of about 100°C. Preferably, a 25-40% solution of the fructan polycarboxylic acid is metered in an amount of 1-4 g/l of water. In addition, preferably 5-20 g/l of 100% NaOH and 1-2 g/l of a non-ionic or anionic detergent, or a combination thereof, are added.

In a reactor, the textile has been deposited and the liquor moves slowly by means of a pump. The duration of the boiling process in a reactor will be between 4 and 8 hours, at a temperature of preferably about 130°C. Preferably, a 25-40% solution of the fructan polycarboxylic acid is metered in an amount of 2-5 g/l of water. In addition, preferably 10-30 g/l of 100% NaOH and 1-3 g/l of a non-ionic or anionic detergent, or a combination thereof, are added.

In a steamer, the liquor is static with respect to the textile. The textile is soaked, pressed between two rollers and then steamed for 2 to 60 minutes, preferably at 100°C. The bath uptake is preferably 100%, that is, 1 liter per  
5 kilogram of textile. Preferably, a 25-40% solution of the fructan polycarboxylic acid is metered in an amount of 5-10 g/l of water. In addition, preferably 30-60 g/l of 100% NaOH and 5-10 g/l of a non-ionic or anionic detergent, or a combination thereof, are added.

10 A next textile treatment where the present method can be applied is bleaching. Bleaching serves to discolor textile by removal of colored constituents through their degradation. Bleaching can take place after a washing process. It is preferred, however, to carry out the  
15 bleaching during a washing process, so as to save time, water and energy. Bleaching is a treatment which is especially used in cotton.

When bleaching is carried out discontinuously, for instance in a dynamic washing/dyeing machine, the  
20 temperature is preferably 80-110°C and the treatment takes 30 to 90 minutes. The liquor ratio is preferably between 1:5 and 1:15. Preferably, a 25-40% solution of the fructan polycarboxylic acid is metered in an amount of 0.5-2 g/l of water. In addition, preferably 1-5 g/l of 100% NaOH and  
25 0.5-2 g/l of a detergent are added. Further, in bleaching, a bleaching agent is present. A suitable example of a bleaching agent is a 35% solution of hydrogen peroxide, which is preferably metered in an amount of 2-10 g/l.

When bleaching is carried out continuously, about 1  
30 liter of water per kilogram of textile is used. The temperature during bleaching is then at 90-100°C and the duration of the treatment is about 2-45 minutes. Preferably, a 25-40% solution of the fructan polycarboxylic acid is metered in an amount of 1-5 g/l of water. In  
35 addition, preferably 5-30 g/l of 100% NaOH, 5-10 g/l of a detergent, and 3-10 g/l of a stabilizer, such as water

glass or organic stabilizers such as polycarboxylic acids or phosphonates, are added. Further, in bleaching, a bleaching agent is present. A suitable example of a bleaching agent is a 35% solution of hydrogen peroxide, which is preferably metered in an amount of 20-70 g/l.

After bleaching, the textile is preferably rinsed and neutralized with acid. For white textile, often a so-called optical whitening agent, such as a stilbene compound, is used during or after bleaching.

When the present method is part of a textile dyeing process, that dyeing process can be carried out with non-pretreated, pre-washed, boiled down or bleached textile. In this case, the present method should ensure in particular that the dyestuffs used do not become insoluble or experience hindrance in their dyeing behavior as a result of the presence of contaminants. The dyestuffs that can be used in a dyeing process with which the present method can be combined include direct dyestuffs, reactive dyestuffs, vat dyestuffs and metal complex dyestuffs.

Direct dyestuffs are bound to textile through hydrogen bridges and Van der Waals' forces. They are chromophores that possess solubilizing groups, such as sulfate or sulfonate groups. In dyeing with a direct dyestuff, preferably a 25-40% solution of the fructan polycarboxylic acid is metered in an amount of 1-3 g/l of water. In addition, it has been found to be of advantage to carry out the dyeing in the presence of 5-20 g/l of salt, preferably sodium sulfate. The temperature in dyeing is preferably between 80 and 100°C. The duration of the dyeing process is normally between 30 and 60 minutes.

Reactive dyestuffs are small chromophores with a reactive group. The dyestuffs are soluble by virtue of a solubilizing group in the molecule, such as a sulfate or sulfonate group. The reactive group, for instance a vinyl sulfone group, binds covalently to the textile in basic medium and so forms a coloration that is fast to washing.

In dyeing with a reactive dyestuff, preferably a 25-40% solution of the fructan polycarboxylic acid is metered in an amount of 1-3 g/l of water. In addition, it has been found to be of advantage to carry out dyeing in the presence of 30-80 g/l of salt, preferably sodium sulfate. In addition, preferably a certain amount of alkali is added. Suitable examples of this are 2-20 g/l of soda, 1-5 g/l of NaOH (100%) and 1-3 g/l of trisodium phosphate. The temperature in dyeing is preferably between 40 and 80°C. The duration of the dyeing process is normally between 60 and 120 minutes.

Vat dyestuffs are anthraquinone- and indigo-like pigments, which, through basic reduction, are brought into solution (the so-called leuco form). In dissolved form, they are added to the textile to be dyed, whereafter the leuco form is undone again through oxidation, which leads to a coloration of a high washing fastness. In this form of dyeing, preferably 25-40% solution of the fructan polycarboxylic acid is metered in an amount of 1-3 g/l of water. In addition, it has been found to be of advantage to carry out the dyeing in the presence of 1-3 g/l of EDTA. Further, preferably 1-10 g/l of NaOH (100%) and 1-3 g/l of dithionite (hydrosulfite) are added. If desired, up to 10 g/l of a salt, preferably sodium sulfate, can be used. The temperature in dyeing is preferably between 40 and 100°C. The duration of the dyeing process is normally between 60 and 120 minutes. As stated, after a dyeing treatment with a vat dyestuff, an oxidation is carried out. This oxidation can proceed in a known manner by the use of peroxide, perborate, percarbonate or oxygen.

Metal complex dyestuffs are used in particular in wool. These substances are chromophores which have been rendered soluble especially with sulfate or sulfonate groups and which also contain metal ions, in particular chromium or copper ions.

A next textile treatment where the present method can be used to remove contaminants from the textile concerns rewashing. As already observed above, after dyeing textile with reactive dyestuffs, a considerable amount of dyestuff, particularly hydrolyzed dyestuff, is left behind on the textile. Because the hydrolyzed dyestuff is not fast to washing, it should be removed to provide a textile with sufficient washing fastness. In a rewashing treatment of textile dyed with reactive dyestuff, the textile is first rinsed with water to remove alkali and salt. Thereupon, it is rewashed, with the fructan polycarboxylic acid being metered in the form of a 25-40% solution in an amount of 1-3 g/l of water. Rewashing preferably takes place at a temperature of 95-100°C for a period of 10-30 minutes. After rewashing, the textile is again rinsed with water to remove residues of the hydrolyzed reactive dyestuff. When the textile has been given a very dark color with a reactive dyestuff, it may be necessary to repeat the rewashing treatment.



## CLAIMS

1. A method for removing contaminants from textile, wherein the textile is treated with a fructan polycarboxylic acid which contains on average at least 0.05 carboxyl groups per monosaccharide unit.
- 5 2. A method according to claim 1, wherein the fructan polycarboxylic acid contains on average between 0.5 and 3 carboxyl groups per monosaccharide unit.
3. A method according to claim 1 or 2, wherein at least 0.05, preferably from 0.2 to 2.0, of every 3
- 10 hydroxymethyl(ene) groups of the fructan on which the fructan polycarboxylic acid is based has been converted into a carboxyl group and at least 0.1, preferably from 0.3 to 2.0, of every 3 hydroxyl groups has been converted into a carboxy-alkoxy or carboxy-acyloxy group.
- 15 4. A method according to claim 3, wherein the hydroxymethyl(ene) groups which have been converted into carboxyl groups and the hydroxyl groups which have been converted into carboxy-alkoxy or carboxy-acyloxy groups are present in the same molecule.
- 20 5. A method according to any one of the preceding claims, wherein the fructan polycarboxylic acid is based on inulin or a derivative thereof.
6. A method according to any one of the preceding claims, wherein the textile is selected from the group of natural
- 25 kinds of textile, preferably from the group of cotton, linen, jute, silk and wool.
7. A method according to any one of the preceding claims, wherein the method is part of a washing, boiling-down, bleaching, dyeing or rewashing treatment of textile.

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 99/00361

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 6 C11D3/22 D06L1/12

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C11D D06L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
E	WO 98 25972 A (COOPERATIE COSUN U.A.) 18 June 1998 (1998-06-18) page 2, last paragraph - page 3, paragraph 1; claims 1-3,13	1-5
A		6,7
A	D.L. VERRAEST ET AL.: "Oxidation and carboxymethylation of sucrose and inulin" ZUCKERIND., vol. 120, no. 9, 1995, pages 799-803, XP002037421 the whole document	1-5
X	WO 91 17189 A (DE NEDERLANDSE ORGANISATIE (...) TNO) 14 November 1991 (1991-11-14) claims 1,7,10	1,5

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

29 July 1999

Date of mailing of the international search report

05/08/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040. Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Van Bellinghen, I

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 99/00361

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9825972 A	18-06-1998	NL 1004738 C AU 5345798 A	11-06-1998 03-07-1998
WO 9117189 A	14-11-1991	NL 9001027 A AT 124960 T AT 174346 T AU 649038 B AU 7696091 A CA 2029542 A CA 2081483 A DE 69020861 D DE 69020861 T DE 69130608 D DE 69130608 T DK 427349 T EP 0427349 A EP 0526494 A ES 2074528 T ES 2126570 T FI 924843 A GR 3017196 T JP 4175301 A US 5326864 A	18-11-1991 15-07-1995 15-12-1998 12-05-1994 27-11-1991 11-05-1991 28-10-1991 17-08-1995 30-11-1995 21-01-1999 27-05-1999 20-11-1995 15-05-1991 10-02-1993 16-09-1995 01-04-1999 26-10-1992 30-11-1995 23-06-1992 05-07-1994